



Specifiche Tecniche *Technical Specification*

Tipo *Grade*

919

Cartone grigio accoppiato liscio
Pasted smooth grey board

Stabilimento *Mill*: Ovaro - Italy

Qualità *Quality*: GK

Gramm. <i>Substance</i>	Spessore <i>Caliper</i>	Volume <i>Bulk</i>
ISO 536	ISO 534	ISO 534
g/m ²	mm	cm ³ /g
1000	1,50	1,50
1060	1,60	1,51
1100	1,70	1,55
1120	1,80	1,61
1190	1,90	1,60
1250	2,00	1,60
1375	2,20	1,60
1430	2,30	1,61
1500	2,40	1,60
1560	2,50	1,60
1750	2,80	1,60
1810	2,90	1,60
1870	3,00	1,60
2125	3,40	1,60
2190	3,50	1,60

Bianco copertina / retro <i>Brightness top/ back</i>	/	ISO 2470 (Photovolt)
Umidità <i>Misture</i>	7%	ISO 287

Tolleranze *Tolerances*

Grammatura <i>Substance</i>	+/- 5%	Media dell'ordine <i>Average of order</i>
Umidità <i>Moisture</i>	+ 2 / - 1	
Spessore <i>Caliper</i>	+/- 5%	Sui singoli campioni (95% dei valori) <i>For singles determinations (95% of values)</i>
Rigidità <i>Stiffness</i>	/	
Grado di bianco <i>Brightness</i>	/	
Condizioni ambientali <i>Test Conditions</i>	T = 23° C +/-1 RH = 50% +/- 2	
Campionamento <i>Sampling</i>	ISO 186	

04 - 2010