

PRESSO
 newsprint paper

10.05.2010

	Parameter	Unit	Value	Comments
1.	Grammage	g/m ²	42,5 ± 1,5 45,0 ± 1,5 48,8 ± 1,5 52,0 ± 1,5	Computerized measurement and adjustment. Calibration of measuring heads and parameter control according to PN-ISO 536:1996.
2.	Moisture	%	7,5 ± 1	Computerized measurement and adjustment. Calibration of measuring heads and parameter control according to PN-ISO 287:1994
3.	Brightness ISO C/2°	%	60,5 ± 2,0	ISO 2470:1999 (Elrepho) top and bottom avg
4.	Opacity 42,5 g/m ² 45,0 g/m ² 48,8 g/m ² 52,0 g/m ²	%	≥ 91 ≥ 92 ≥ 93 ≥ 94	ISO 2471:1998 (Elrepho) top and bottom avg
5.	Smoothness Bekk	s	≥ 50	PN-ISO 5627:1998 top and bottom avg
6.	Stretching force 42,5 g/m ² 45,0 g/m ² 48,8 g/m ² 52,0 g/m ²	N	≥ 29 ≥ 30 ≥ 30 ≥ 32	PN-ISO 1924-1:1998
7.	Elongation MD 42,5 g/m ² 45,0 g/m ² 48,8 g/m ² 52,0 g/m ²	%	1,2 ± 0,2 1,3 ± 0,2 1,4 ± 0,3 1,4 ± 0,3	PN-ISO 1924-1:1998

Conditioning at: RH 50 ± 2 % temp. 23 ± 1 °C PN-EN 20187:2000