

Future multitech

Technical details

Description:	Woodfree uncoated all-round paper. Read more >>
Printing method:	Fax, Copying, B/W inkjet printing, B/W laser printing
End use:	Memos, Fax papers, Reports, Correspondence
Furnish:	Chemical pulp
Finish:	Machine finished
Wrapping:	Strong moisture proof polyethylene laminated kraft paper
Production Units:	Kymi, Nordland

Technical Target Values

Basis Weight (g/m ²)	75.0	80.0	90.0	100.0
Bulk (ISO 534) (cm ³ /g)	1.4	1.32	1.3	1.3
Roughness Bendtsen (ISO 8791-2) (ml/min)	230	200	200	200
Opacity ISO (2471) (%)	93	94	95	95.5
CIE Whiteness (%)	164	164	164	164
Thickness (ISO 534) (μm)	105	106	117	130